

## Product Data Sheet

# PROTAN QUALITY 953 Black out treatment

### Suitable applications

Soft skin buildings and inner cover

### Technical characteristics:

Properties	Test method	Typical values
Base fabric		Polyester, 1100dtex, plain weave
Coating		PVC
Yarn construction warp-weft		8x9
Width, cm	EN 1848-2	204
Weight, g/m2	EN 1849-2	700
Tear resistance (L/T), N	DIN 53356	400/350
Tensile strength (L/T), N/5cm	EN 12311-2	2600/2500
Elongation (L/T), %	EN 12311-2	≥15
Adhesion, N/5cm	DIN 53357	≥80
Temperature resistance, °C	EN 495-5	-30
Flame retardant	EN ISO 11925-2	Satisfactory

Typical values are average values from the production.

### Standard colour:

Protan colour code: 001 (white).  
Other colours on request